



ENNIS FABRICS



FRANKLIN 2nd EDITION



36 CERULEAN



909 BLACK



61 SNOW



601 OYSTER



97 CINDER



92 PLATINUM



908 SMOKE



903 SEAL



99 STEEL



94 METAL



9004 CHARCOAL



67 FAWN



47 CAMEL



609 MINK



8009 CHOCOLATE



202 SAGE



208 AVOCADO



84 BRASS



308 PETROL



306 IMPERIAL



34 TEAL



205 LIMA




82 EMERALD



3009 MIDNIGHT



1008 DEEP PURPLE



108 ORCHID



105 BLUSH



14 THEATRE RED



FRANKLIN

2nd EDITION



A velvet look, with a soft hand and great price point.

SPECIFICATIONS* / SPÉCIFICATIONS*

ABRASION†	235,000 Double Rubs
CONTENT / CONTENU	100% Polyester
BACKING CONTENT / COMPOSITION DU REVERS	100% Polyester
COLORS / COULEURS	28 available <i>[disponible]</i>
CROCKING / SOLIDITÉ AU FROTTEMENT	AATCC 8: Dry <i>[Sec]</i> = Class (e) 4, Wet <i>[Mouillé]</i> = Class (e) 4.5
FIRE RETARDANCY	CALTB117-2013, NFPA 260 Class (e) 1, NFPA 701, UFAC Class 1
PILLING / BOULOCHAGE	ASTM D3511: Class (e) 5
SEAM SLIPPAGE / GLISSEMENT DE LA COUTURE	ASTM D4034: Warp <i>[Chaîne]</i> = 83lbs, Fill <i>[Trame]</i> = 109lbs.
UV/LIGHTFASTNESS / RÉSISTANCE AU RAYON UV	AATCC 16 - Grade 4, hours <i>[heures]</i>
WEIGHT / POIDS	18.47 oz./lin. yd <i>[vg]</i> 12.10 oz./yd ² <i>[vg²]</i>
WIDTH / LARGEUR	56 in. [142 cm]
ROLL SIZE / TAILLE DU ROULEAU	45 yd <i>[vg]</i> [41 m]
CLEANING INSTRUCTIONS / INSTRUCTIONS DE NETTOYAGE	WS—Clean fabrics with water-based cleaning agents only do not use Solvent cleaners <i>[Détergent à base d'eau]</i>

* This term and any corresponding data refer to typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions. This information is offered for your general guidance only. It's accurate to the best of our knowledge and is not intended to relieve the user from its responsibility to investigate and understand other pertinent sources of information and to comply with all laws and procedures applicable to the safe handling and use of this material. Final determination of the suitability of any product for an application rests with the user.

† Results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

* Les résultats rapportés d'après la norme ci-dessus ne définissent pas nécessairement les risques que représente ce matériau dans des conditions réelles d'incendie. Ces renseignements sont offerts à titre consultatif seulement. Ils sont précis, aux mieux de nos connaissances, et ne sont pas destinés à dégager l'utilisateur de sa responsabilité d'étudier et de comprendre les autres sources pertinentes de renseignements, ni de se conformer à toutes les lois et procédures relatives à la manipulation et à l'utilisation sécuritaires de ce matériau. La décision finale du type d'application du produit appartient à l'utilisateur.

† Les doubles frottements supérieurs à 100 000 ne sont pas un indicateur d'une durée de vie accrue pour un produit.



FRANKBC2BC
0123



CANADA ENGLISH 800 663 6647 - FRANÇAIS 888 663 6647
USA 877 953 6647
FAX 888 274 2910
ORDERS@ENNISFABRICS.COM
ENNISFABRICS.COM